

**"Junction for photovoltaic cells, optical sensors or
the like"**

The present invention relates to junctions for
5 photovoltaic cells, optical sensors or the like.

The photovoltaic effect is the conversion of elec-
tromagnetic radiation (especially light) into electric
current, which occurs in some materials, such as sili-
con and germanium, known as "semiconductors".

10 Devices operating on the basis of said principle
are known as "photovoltaic cells". They are currently
used for instance as energy supply for calculating ma-
chines and solar energy watches, and in the field of
nuclear physics as photon detectors (gamma rays). On
15 artificial satellite large solar panels supply energy
to on-board instruments.

The conductive capacity of semiconductors strongly
depends on their purity and can be increased by intro-
ducing impurities into the latter (doping). By placing
20 close to one another two semiconductors doped so that
one has an excess of positive charges (known as holes)
and the other one an excess of negative charges, a p-n
junction is obtained. The semiconductor absorbs part of
the photons belonging to the light illuminating it.
25 When a photon is absorbed, its energy releases an elec-
tron (which can move within the semiconductor) and gen-
erates at the same time a positive hole. The electron
and the hole are spontaneously separated by the elec-
tronic field of the junction and are stored in two op-
30 posite areas so as to generate a potential difference
at the ends of the device. By connecting said two ends
to a circuit electric current is obtained. The photo-
voltaic cell is the device that can convert the energy
of light radiations directly into electric energy. It
35 basically consists of two thin layers of semiconductor

material (crystalline or amorphous silicon or other substances): a n-type layer (which tends to collect electrons), and a p-type layer (which tends to collect positive charges or holes). The photovoltaic cell is
5 usually equipped with an antireflection coating and with two electric contacts, an upper one and a lower one.

During operation, in the contact area (junction) between the two semiconductors there is an electric
10 field due to the different nature of said two materials. When the contact area is struck by sunlight, i.e. by photons, electrons (the outer ones in silicon atoms) are "mobilized" and pushed into layer n by the electric field. Every electron getting released gives simultane-
15 ously rise to a positive charge which - still due to the electric field - is pushed into layer p. The connection of both layers to an outer circuit results in a circulation of electrons, i.e. in a direct electric current, between n and p.

20 Solar cells or optical sensors with porous silicon have also been proposed, using so-called "Schottky" junctions, for instance with gold or aluminum.

The present invention aims at carrying out a junction of this type, which is able to highly increase
25 cell efficiency or to obtain a particularly sensitive sensor.

In order to achieve said aim, the junction according to the present invention is characterized in that it has the features referred to in the appended claim
30 1.

Thanks to said features the surface of the junction is greatly increased, so as to obtain a high increase in cell efficiency.

The invention will now be described with reference
35 to the accompanying drawings, provided as a mere non-

limiting example, in which:

- Figure 1 is a schematic view of a silicon-metal junction according to the prior art,

- Figure 2 is a magnified scale view of a detail of Figure 1 modified according to the teachings of the present invention,

- Figure 3 shows a further embodiment of the invention, and

- Figure 4 shows a further embodiment.

10 Figure 1 shows schematically a junction comprising a silicon layer 1 and a metal layer 2, for instance gold or aluminum. According to a technique known per se, the silicon layer 1 has a porous structure whose pores have a micrometric or nanometric size
15 (microporous or nanoporous silicon). According to the prior art, the metal is deposited by thermal evaporation onto the silicon layer 1. As a consequence of said application the metal does not penetrate into silicon pores and the useful junction is still the one on the
20 surface. The two layers are connected to two electrodes 3, 4.

 According to the invention, techniques known per se, for instance sol gel deposition techniques or more generally so-called CSD techniques ("Chemical Solution
25 Deposition"), are used to let the metal 2 penetrate into the pores of microporous or nanoporous silicon, so as to fill them partially (Figure 2) or completely (Figure 4).

 An object of the present patent is also a new
30 technique for filling silicon pores: porous silicon is usually obtained by anodization in a bath of hydrofluoric acid. Typical currents for obtaining nanoporous silicon are of about 10 mA/cm². After a normal anodization step, whose duration depends on the porous thickness desired for silicon, a solution of gold chloride
35

is introduced into the bath. Gold reduces on silicon: the presence of holes simplifies the penetration of gold chloride into the pores where gold deposits. Reduction occurs spontaneously but can be favored by in-
5 verting cell polarity during the final step of the process. Gold chloride is just an example, though other solutions also with other metals are possible.

The phenomenon can be further favored by making the substrate 1 completely porous (Figure 4), with
10 through pores, and by arranging a cathode C and anode A after and before said substrate, thus forcing metal ions (arrow F) to go through it. A part of them reduces in the porous substrate, which can be kept at the same potential as the cathode or at a floating potential.

15 Thus, every square centimeter of silicon corresponds to a few useful square meters of junction.

The same principle can obviously apply to electromagnetic radiations having different wavelength, for instance for thermophotovoltaic applications, by suitably
20 choosing materials depending on the relevant frequency range.

According to a further feature of the invention, in order to increase at the same time surface transmittance and conductivity, silicon pores can be filled
25 with the optimal junction material and then an ITO layer (Indium Tin Oxide) can be deposited onto the surface.

Obviously, though the basic idea of the invention remains the same, construction details and embodiments
30 can widely vary with respect to what has been described and shown by mere way of example, however without leaving the framework of the present invention.